

MEMORY

BIANCO



GRIGIO



MIELE



TORTORA



FORMATI - Sizes



15,3x100
15,3x100 **R11** (Grigio - Tortora)



30x60 (Miele - Tortora)



	15,3x100	15,3x100 R11	30x60
 BIANCO	S9480	-	-
 GRIGIO	S9483	S9483A	-
 MIELE	S9481	-	S10481
 TORTORA	S9484	S9484A	S10484
COD. P	36	36	29
▼ SPESSORE ▲	10 mm	10 mm	8 mm

CARATTERISTICHE TECNICHE TECHNICAL CHARACTERISTICS

CONSIGLI DI POSA PATTERNS

V3

**INTENSA VARIAZIONE**

Substantial Variation
Variation Intensive
Intensive Variation


PEI

**COEFFICIENTE DI RESISTENZA ALL' ABRASIONE**


Coefficient of resistance to abrasion
Coefficient de résistance à l'abrasion
Abriebhärteskoeffizient



grigio




15,3x100
30x60



100% 15,3x100
100% 30x60


100%
100%

PEZZI SPECIALI SPECIAL PIECES




SBT + COD. Battiscopa
6,5x100

10x  11



CR + COD. Gradone
15,3x100+3+3

4x  101



ACR + COD. Angolo Gradone
15,3x100+3+3 *1CP

1x  107

*Per informazioni approfondite sui pezzi speciali, consultare la sezione dedicata a fine catalogo.

IMBALLI PACKING

	pcs/box	mq/box	kg/box	box/pallet	mq/pallet	kg/pallet
15,3x100	8	1,23	24,00	42	51,66	1.028,00
30x60	8	1,44	24,80	40	57,60	1.022,00



Main Laboratory Sassuolo

Centro di Ricerca, Sperimentazione, Consulenza e Controllo Qualità

Scandiano, 12/16/2014



TEST REQUESTED BY: **CERAMICA SAVOIA ITALIA S.r.l.**

Via Ghiarola Nuova, 77
41042 Fiorano Modenese
(MO)

Confidential Test Report N. 5182/2014 /I

Our ref.num.: 13681

Date of request: 12/12/2014

TEST SUBJECT MATERIAL

Identified by client as:

"Paver tiles 15,3x100 cm marked:

MEMORY BIANCO"

Source

Submitted to Laboratory by Client

Date Received

12/12/2014

Time of test execution

start: 12/16/2014

end: 12/16/2014

Detailed of test / method description / test procedure

BOT 3000 "Dynamic Coefficient of Friction (DCOF)"
(Ref. 9.6, Standard ANSI A137.1:2012)

The report relates only to the sample(s) tested. This report must not be reproduced in part without the written permission of Main Laboratory Sassuolo, nor used in any way as to lead to misrepresentation of the results or their implications.

Page 1 of 2



Confidential Test Report N. 5182/2014 /I Page 2 of 2

Date 12/16/2014

CERAMICA SAVOIA ITALIA S.r.l.

Test specimen

"Paver tiles 15,3x100 cm marked:

MEMORY BIANCO"

BOT 3000 "Dynamic Coefficient of Friction (DCOF)"

(Ref. 9.6, Standard ANSI A137.1:2012)

TEST PROCEDURE: must be used sensor SBR rubber with characteristics standardized (par. 9.6.1.1.2 and note 3).

Sensor SBR must be controlled using a surface standard before the test.

Three (3) pieces of tile are tested in all four directions (1-2-3-4).

Testing was done in the wet condition using 0.05% SLS water

Testing was conducted in a laboratory at temperature of 20 ± 2 °C and $50 \pm 5\%$ relative humidity.

Instrument used is BOT 3000 of the Regan Scientific Instruments.

Note: considering the size of the sample both calibration and the test was executed on a path of 4 inch, because the longer practicable (as described in paragraph 9.6.1.1)

Dynamic Coefficient

DCOF wet of friction Standard Tiles

Before the test	0,29
After the test	0,30

Test conditions: wet surface (solution SLS 0,05 %), rubber sensor

No.	Position				Average
	1	2	3	4	
1	0,63	0,61	0,65	0,63	0,63
2	0,64	0,62	0,65	0,64	0,64
3	0,65	0,65	0,64	0,64	0,65



THE DIRECTOR
(M. Samioli)